

Plastocrete®-R6

Water-reducing and set retarding concrete admixture

Construction

Product Description

Plastocrete®-R6 is a set retarding concrete admixture with plasticising effect. Substantial water reduction can be achieved without loss of workability.

Uses

Plastocrete®-R6 is used where high quality concrete is required in difficult conditions, such as:

- High temperatures
 - Long distance between batching plant and site
 - Ready-mix concrete
 - Prestressed concrete
- and whenever high quality dense concrete is required

Characteristics / Advantages

- High slump retention
- Improved workability without increasing water content
- Increased strengths
- Reduced shrinkage and creep
- Improved surface finish
- Chloride free – does not attack reinforcement

Product Data

Form

Appearance / Colour Brown liquid

Packaging 20 litre pails, 206 litre drums and 1,000 litre tanks

Storage

Storage Conditions / Shelf Life 12 months from the date of production if stored properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5°C and +35°C. Protect from direct sunlight.

Technical Data

Chemical Base Special organic agents



System Information

Application Details

Dosage	<p>Plastocrete®-R6 is normally dosed at 200 – 800 ml per 100 kg of cement. Actual dosage rate required will depend on:</p> <ul style="list-style-type: none"> ■ Effect required (slump retention, strength, etc.) ■ Quality of cement and aggregates ■ Water : cement ratio ■ Temperature <p>It is advisable to carry out trial mixes to establish the dosage required.</p> <p>Plastocrete®-R6 is compatible with all types of Portland cement including Sulphate Resistant Cement (S.R.C.) and blends of ground granulated blast furnace (G.G.B.S.) slag, fly ash with OPC. For more specific requirements, advice is available from our Technical Service Department.</p>
---------------	---

Application Instructions

Dispensing	Plastocrete®-R6 should be dispensed directly into the mixing water prior to the addition of other concrete components such as coarse aggregates, sand and cement. Accurate dispensing equipment is readily available from Sika.
Cleaning of Tools	Clean all tools and application equipment with water immediately after use. Hardened and/or cured material can only be removed mechanically.
Value Base	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Health and Safety Information	For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent Material Safety Data Sheet (available on request) containing physical, ecological, toxicological and other safety-related data.
--------------------------------------	---

Legal Notes	<p>The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.</p>
--------------------	---



Sika Kimia Sdn Bhd
 Lot 689 Nilai Industrial Estate
 71800 Nilai, Negeri Sembilan DK
 MALAYSIA

Phone: +6 06 799 1762
 Fax: +6 06 799 1980
 e-mail: info@my.sika.com
www.sika.com.my

