

SikaLatex® SP

Water-resistant bonding agent and mortar-strengthening additive

Product Description

SikaLatex® SP is a synthetic rubber emulsion for adding to cement mortars, where good adhesion and water resistance are required. It is suitable for tropical conditions.

Uses

SikaLatex® SP is a high quality emulsion that substantially increases the qualities of cement mortars such as:

- Thin layer patching mortars
- Renders
- Floor screeds
- Concrete repair mortars
- Abrasion resistant linings
- Tile fixing mortars
- Masonry mortars

Characteristics / Advantages

- Extremely good adhesion
- Reduced shrinkage
- Greater elasticity
- Excellent water resistance
- Increased abrasion resistance
- Improved chemical resistance
- Non-corrosive
- Ready for use
- Does not re-emulsify, even in high alkaline conditions

Product Data

Form

Appearance / Colour Milky white liquid

Packaging 5 ltr pails, 20 ltr pails and 200 ltr drums

Storage

Storage Conditions / Shelf Life 12 months from the date of production if stored properly in original, unopened and undamaged packaging in dry conditions. Keep away from direct sunlight.



Technical Data

Chemical Base Styrene Butadiene Latex Emulsion

Density 1.00 kg/ltr ± 0.01

Chloride Content Nil

System Information

Application Details

Consumption SikaLatex[®] SP is generally added to the clean mixing water within the range of 1:1 – 1:2.5 for all applications, apart from sprayed-on renders, where a bonding slurry should be applied.

Subsequent mortar application must be carried out while the bonding coat is still wet.

Substrate Quality The concrete must be clean, sound and free of all loose and friable material, cement laitance, oil, grease, etc.

Substrate Preparation Absorbent surfaces should be saturated thoroughly.

Application Instructions

Mixing Aggregates should be well graded and thoroughly washed. Sand particle sizes should correspond to the thickness of mortar to be applied and required surface finish.

Mortar Thickness	Aggregate Size
< 2 mm	0 - 0.5 mm
2 – 5 mm	0 - 1.0 mm
5 – 15 mm	0 - 3.0 mm
> 15 mm	0 - 7.0 mm

Application Method / Tools

Bonding Slurry

SikaLatex[®] SP : water = 1:1, mixed with fresh cement to a creamy consistency, should be brushed onto the prepared surface.

High-Performance Render

Mix SikaLatex[®] SP : water in a 1:1 ratio. Use a maximum of 25 ltr of this solution in a mix containing 50 kg of cement and 150 kg of sand. This will yield approximately 100 litres of mortar which will cover 10 m² to a thickness of 10 mm.

Cleaning of Tools

Clean all tools and application equipment with water immediately after use. Hardened and/or cured material can only be mechanically removed.

Notes on Application / Limitations

- Renderings and floor toppings should be allowed to cure correctly
 - Avoid excessive air-entrainment through over-mixing
 - Never use neat SikaLatex[®] SP or SikaLatex[®] SP with water as a bonding agent – always add cement and sand
-

Value Base

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet (available upon request) containing physical, ecological, toxicological and other safety-related data.

Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Sika Kimia Sdn Bhd
Lot 689 Nilai Industrial Estate
71800 Nilai, Negeri Sembilan DK
MALAYSIA

Phone: +6 06 799 1762
Fax: +6 06 799 1980
e-mail: info@my.sika.com
www.sika.com.my

