

SikaTop® Armatec®-110 EpoCem®

Bonding Primer and Reinforcement Corrosion Protection

Construction

Product Description SikaTop® Armatec®-110 EpoCem® is a cementitious, epoxy resin compensated three-component coating material with corrosion inhibitor, used as bonding primer and reinforcement corrosion protection. SikaTop® Armatec®-110 EpoCem® meets the requirement of EN 1504-7.

Uses

- Suitable for control of anodic areas (Principle 11, method 11.1 of EN 1504-9)
- Suitable in concrete repair as corrosion protection for reinforcement.
- Suitable as a bonding primer on concrete and mortar

Characteristics / Advantages

- Contains EpoCem® technology - improved bonding agent
- Extended open times for repair mortars
- Compatible with most Sika® MonoTop® repair mortars
- Excellent adhesion to concrete and steel
- Contains corrosion inhibitor
- Certified for application under dynamic load conditions
- Good resistance to water and chloride penetration
- High shear strength
- Long pot life
- Easy to mix
- Can be brushed on or applied using spray gun

Tests

Approval / Standards

CE Requirement:
BAM, Federal Institute for Material Research and Testing, Berlin, Germany - Initial Type Test report in accordance with EN 1504-7, Nr. BAM VI.1 / 14574-2, dated 13th May 2009.

BAM, Federal Institute for Material Research and Testing, Berlin, Germany - Application under live dynamic loading - Nr. VII.1 / 126904/1, dated 1st of July 2008.

Polymer Institute, Flörsheim-Wicker, Germany- Determination of shear failure resistance between old and new concrete, Nr. P 2965, dated 30th September 2002.

Product Data

Form

Appearance / Colour

Mixed components dark grey.

Component A: white liquid

Component B: colourless liquid

Component C: dark grey powder



Packaging	20 kg A (1.14kg) + B (2.86kg) + C (16kg)
------------------	--

Storage

Storage Conditions / Shelf-Life	12 months from date of production if stored properly in undamaged original sealed packaging, in dry cooled conditions between +5°C and +25°C.
--	---

Technical Data

Chemical Base	Portland cement, epoxy resin, selected aggregates and additives	
Density	A+B+C density: ~2.0 kg/l at 23°C	
Thermal Expansion Coefficient	18 x 10 ⁻⁶ m/(m x °C)	(EN 1770)
Carbon Dioxide Diffusion Resistance	μCO ₂ ~40'000	
Water Vapour Diffusion Resistance	μH ₂ O ~700	

Mechanical / Physical Properties

	20°C in lab conditions
Adhesive Bond	> 1.5 N/mm ² after 28 days
Shear Strength	~16 N/mm ² (waiting time 2 hours)
Elastic Modulus	~16,400 N/mm ² (static)

Requirements Requirements as per EN 1504-7

	Test Method	Results (ITT results)	Requirements
Corrosion Protection	EN 15183	Pass	Coated zones of the steels are free of corrosion and if rust creep at the ground plate edge < 1 mm.

System Information

System Structures	SikaTop® Armatec®-110 EpoCem® is part of the Sika® repair system complying with the relevant part of European Standard EN 1504 and comprising of: <ul style="list-style-type: none"> - SikaTop® Armatec®-110 EpoCem®: Bonding primer and reinforcement corrosion protection - Sika® MonoTop®-352 N / -352 NFG: Light weight repair mortar - Sika® MonoTop®-412 N / -412 NFG: Structural repair mortar - Sika® MonoTop®-723 N: Pore sealer and levelling mortar
--------------------------	--

Application Details

Consumption	<p><i>As reinforcement corrosion protection coating:</i> ~ 2 kg per m² and application layer (~ 1mm thick) In total minimum 2 layer thickness (~ 2mm thick)</p> <p><i>As a bonding primer, substrate:</i> > 1.5 to 2.0 kg per m² /mm dependent on substrate conditions</p>
Substrate Quality	<p><i>Concrete:</i> The concrete shall be free from dust, loose material, surface contamination and materials which reduce bond or prevent suction or wetting by repair materials.</p> <p><i>Steel reinforcement:</i> Rust, scale, mortar, concrete, dust and other loose and deleterious material which reduces bond or contributes to corrosion shall be removed</p>

Substrate Preparation	<p><i>Concrete:</i> Delaminated, weak, damaged and deteriorated concrete and where necessary sound concrete shall be removed by suitable means.</p> <p>The surface shall be thoroughly pre-wetted and not be allowed to dry before application of the concrete repair mortar. The surface shall achieve a dark matt appearance without glistening and surface pores and pits shall not contain water.</p> <p><i>Steel reinforcement:</i> Surfaces shall be prepared using abrasive blast cleaning techniques or high pressure water-blasting.</p>								
Application Conditions / Limitations									
Substrate Temperature	+5°C min.; +30°C max.								
Ambient Temperature	+5°C min.; +30°C max.								
Application Instructions									
Waiting Time	<p><i>Maximum waiting time before application of repair mortar</i></p> <p>Sika repair mortars and non-fast setting concrete can be applied on SikaTop® Armatec®-110 EpoCem® within a maximum time of:</p> <p>6 hours with + 30°C 5 hours with +20°C 2 hours with +10°C 1 hour with +5°C</p>								
Mixing	<p>SikaTop® Armatec®-110 EpoCem® can be mixed with a low speed (<250 rpm) electric drill mixer.</p> <p>Shake components A and B thoroughly before opening. Pour liquid components A+B into a suitable mixing vessel and mix for 30 seconds. While still mixing components A+B slowly add powder component C. Mix the three components together for a minimum 3 minutes, minimising addition of air. Leave to stand for 5 - 10 minutes until mixed coating material exhibits a brush-able, weakly dripping consistency.</p> <p>DO NOT ADD WATER!</p>								
Application Method / Tools	<p><i>As reinforcement corrosion protection:</i> Apply first layer approx. 1 mm thick, using medium hard brush or spray gun to the cleaned reinforcement. Apply 2nd layer when the first coat is hard to the fingernail (~2 - 3 hours at +20°C).</p> <p><i>As a bonding primer:</i> Apply using medium hard brush or spray gun to prepared substrate. To achieve good bond, SikaTop® Armatec®-110 EpoCem® must be applied well into the substrate, filling all pores.</p> <p>Freshly applied SikaTop® Armatec®-110 EpoCem® must be protection against contamination and rain until application of the repair mortar.</p> <p><i>Application under dynamic loading:</i> SikaTop® Armatec®-110 EpoCem® has been tested with the following Sika repair mortars and is certified for dynamic loading applications. Refer to separate sheets for further information.</p> <p><i>Dry Spray Process:</i></p> <table border="0"> <tr> <td>Corrosion Protection:</td> <td>SikaTop® Armatec®-110 EpoCem®</td> </tr> <tr> <td>Repair and overlay:</td> <td>SikaCem®-Gunite 133</td> </tr> </table> <p><i>Wet Spray Process:</i></p> <table border="0"> <tr> <td>Corrosion Protection and/or Bonding primer:</td> <td>SikaTop® Armatec®-110 EpoCem®</td> </tr> <tr> <td>Repair and Overlay:</td> <td>Sika® MonoTop®-412 N/ -412 NFG</td> </tr> </table>	Corrosion Protection:	SikaTop® Armatec®-110 EpoCem®	Repair and overlay:	SikaCem®-Gunite 133	Corrosion Protection and/or Bonding primer:	SikaTop® Armatec®-110 EpoCem®	Repair and Overlay:	Sika® MonoTop®-412 N/ -412 NFG
Corrosion Protection:	SikaTop® Armatec®-110 EpoCem®								
Repair and overlay:	SikaCem®-Gunite 133								
Corrosion Protection and/or Bonding primer:	SikaTop® Armatec®-110 EpoCem®								
Repair and Overlay:	Sika® MonoTop®-412 N/ -412 NFG								
Cleaning of Tools	Clean all tools and application equipment with water immediately after use. Hardened material can only be mechanically removed.								
Potlife	~ 3 Hours at +20°C								

Notes on Application / Limitations	<ul style="list-style-type: none"> - Refer to the Method Statement for Concrete Repair using Sika® MonoTop® system for more information regarding substrate preparation or refer to the recommendations provided in EN 1504-10 - Avoid application in direct sun and/or strong wind and/or rain. - Do not add water over recommended dosage. - Apply only to sound, prepared substrates. - NOT recommended for use with fast setting concrete or mortars e.g. Sika® MonoTop®-211 FG / RFG
Curing Details	
Curing Treatment	Protect the fresh mortar from rain while the material has not yet set.
Value Base	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.
Health and Safety Information	For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.
Legal Notes	The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Sika Kimia Sdn Bhd
 Lot 689 Nilai Industrial Estate
 71800 Nilai, Negeri Sembilan DK
 MALAYSIA

Phone: +6 06 799 1762
 Fax: +6 06 799 1980
 e-mail: info@my.sika.com
www.sika.com.my

