

# Sikadur®-41 CF Normal

## 3-part thixotropic epoxy patching mortar

### Product Description

Sikadur®-41 CF Normal is a thixotropic, three part patching and repair mortar, based on a combination of epoxy resins and special fillers, designed for use at temperatures between +10°C and +30°C..

### Uses

As repair and bonding mortar for:

- Concrete elements
- Hard natural stone
- Ceramics, fiber cement
- Mortar, Bricks, Masonry
- Steel, Iron, Aluminium
- Wood
- Polyester, Epoxy
- Glass

As a repair mortar:

- Filling of cavities and voids
- Vertical and overhead use

As an abrasion and impact resistant wearing course.

Joint filling and crack sealing:

- Joint and crack arris / edge repair

### Characteristics / Advantages

Sikadur®-41 CF Normal has the following advantages:

- Easy to mix and apply
- Suitable for dry and damp concrete surfaces
- Very good adhesion to most construction materials
- High strength
- Thixotropic: non-sag in vertical and overhead applications
- Hardens without shrinkage
- Different coloured components (for mixing control)
- No primer needed
- High initial and ultimate mechanical strength
- Good abrasion resistance
- Good chemical resistance

### Approval / Standards

Testing according to EN 1504-3.

### Product Data

#### Appearance /Colours

Part A: white  
Part B: dark grey  
Part C: sand  
Parts A+B+C mixed: concrete grey

#### Packaging

10 kg (A+B+C) Pre-batched unit, pallets of 480 kg (48 x 10 kg).

Construction



## Storage

<b>Storage Conditions/ Shelf-Life</b>	24 months from date of production if stored properly in original unopened, sealed and undamaged packaging, in dry conditions at temperatures between +5°C and +30°C. Protect from direct sunshine.
---	--

## Technical Data

<b>Chemical Base</b>	Epoxy resin.
<b>Density</b>	1.85 ± 0.1 kg/l (Part A+B+C mixed) (at +23°C) (evacuated)
<b>Sag Flow</b>	On vertical surfaces it is non-sag up to 20 mm thickness. (According to EN 1799)
<b>Layer Thickness</b>	60 mm max. When using multiple units, one after the other. Do not mix the following unit until the previous one has been used in order to avoid a reduction in handling time.
<b>Change of Volume</b>	Shrinkage: Hardens without shrinkage.
<b>Thermal Expansion Coefficient</b>	Coefficient W: 3.5 x 10 <sup>-5</sup> per °C (Temp. range +23°C - +60°C) (According to EN 1770)
<b>Thermal Stability</b>	Heat Deflection Temperature (HDT): HDT = +49°C (7 days / +23°C) (According to ISO 75) (thickness 10 mm)

## Mechanical / Physical Properties

### Compressive Strength (According to DIN EN 196)

Curing time	Curing temperature		
	+10°C	+23°C	+30°C
1 day	13 - 23 N/mm <sup>2</sup>	57 - 67 N/mm <sup>2</sup>	67 - 77 N/mm <sup>2</sup>
3 days	45 - 55 N/mm <sup>2</sup>	74 - 84 N/mm <sup>2</sup>	76 - 86 N/mm <sup>2</sup>
7 days	59 - 69 N/mm <sup>2</sup>	77 - 87 N/mm <sup>2</sup>	77 - 87 N/mm <sup>2</sup>

### Flexural Strength (According to DIN EN 196)

Curing time	Curing temperature		
	+10°C	+23°C	+30°C
1 day	6 - 12 N/mm <sup>2</sup>	17 - 27 N/mm <sup>2</sup>	20 - 30 N/mm <sup>2</sup>
3 days	14 - 24 N/mm <sup>2</sup>	21 - 31 N/mm <sup>2</sup>	25 - 35 N/mm <sup>2</sup>
7 days	26 - 36 N/mm <sup>2</sup>	33 - 43 N/mm <sup>2</sup>	33 - 43 N/mm <sup>2</sup>

### Tensile Strength (According to ISO 527)

Curing time	Curing temperature		
	+10°C	+23°C	+30°C
1 day	2 - 6 N/mm <sup>2</sup>	11 - 19 N/mm <sup>2</sup>	12 - 22 N/mm <sup>2</sup>
3 days	12 - 18 N/mm <sup>2</sup>	13 - 21 N/mm <sup>2</sup>	14 - 24 N/mm <sup>2</sup>
7 days	13 - 19 N/mm <sup>2</sup>	15 - 22 N/mm <sup>2</sup>	16 - 26 N/mm <sup>2</sup>

### Bond Strength (According to EN ISO 4624 and EN 1542 and EN 12188)

Time	Temperature	Substrate	Bond strength
7 days	+10°C	Concrete dry	> 4 N/mm <sup>2</sup> *
7 days	+10°C	Concrete moist	> 4 N/mm <sup>2</sup> *
7 days	+10°C	Steel	4 - 8 N/mm <sup>2</sup>

<b>..cont'd Bond Strength</b>	7 days	+23°C	Steel	13 - 17 N/mm <sup>2</sup>
*100% concrete failure.				
<b>E-Modulus</b>	Tensile: ~ 4'000 N/mm <sup>2</sup> (14 days at +23°C)		(According to ISO 527)	
	Compressive: ~ 9'000 N/mm <sup>2</sup> (14 days at +23°C)		(According to ASTM D695)	
<b>Elongation at Break</b>	0.2 ± 0.1% (7 days at +23°C)			(According to ISO 75)

## System Information


### Application Details

<b>Consumption / Dosage</b>	The consumption of Sikadur <sup>®</sup> -41 CF Normal is ~ 2.0 kg/m <sup>2</sup> per mm of thickness.
<b>Substrate Quality</b>	Mortar and concrete must be older than 28 days (depends on minimal requirement of strengths). Verify the substrate strength (concrete, masonry, natural stone). The substrate surface (all types) must be clean, dry and free from contaminants such as dirt, oil, grease, existing surface treatments and coatings etc. Steel substrates must be de-rusted similar to Sa 2.5 The substrate must be sound and all loose particles must be removed.
<b>Substrate Preparation</b>	Concrete, mortar, stone, bricks: Substrates must be sound, dry, clean and free from laitance, ice, standing water, grease, oils, old surface treatments or coatings and all loose or friable particles must be removed to achieve a laitance and contaminant free, open textured surface. Steel: Must be cleaned and prepared thoroughly to an acceptable quality i.e. by blastcleaning and vacuum. Avoid dew point conditions.

### Application Conditions / Limitations

<b>Substrate Temperature</b>	+10°C min. / +30°C max.
<b>Ambient Temperature</b>	+10°C min. / +30°C max.
<b>Material Temperature</b>	Sikadur <sup>®</sup> -41 CF Normal must be applied at a temperatures between +10°C and +30°C.
<b>Substrate Moisture Content</b>	When applied to mat moisture concrete, brush the adhesive well into substrate.
<b>Dew Point</b>	Beware of condensation! Substrate temperature during application must be at least 3°C above dew point.

### Application Instructions

<b>Mixing</b>	Part A : B : C = 2 : 1 : 2.5 by weight Part A : B : C = 2 : 1 : 3.4 by volume
<b>Mixing Time</b>	 <p>Pre-batched units: Mix parts A+B together for at least 3 minutes with a mixing spindle attached to a slow speed electric drill (max. 300 rpm) until the material becomes smooth in consistency and a uniform grey colour. Then add part C and continue until mixture is homogeneous. Avoid aeration while mixing. Then, pour the whole mix into a clean container and stir again for approx. 1 more minute at low speed to keep air entrapment at a minimum. Mix only that quantity which can be used within its potlife.</p>

<b>Application Method / Tools</b>	<p>When using a thin layer adhesive, apply the mixed adhesive to the prepared surface with a spatula, trowel, notched trowel, (or with hands protected by gloves). When applying as a repair mortar use some formwork.</p> <p>When using for bonding metal profiles onto vertical surfaces, support and press uniformly using props for at least 12 hours, depending on the thickness applied (not more than 5 mm) and the room temperature.</p> <p>Once hardened check the adhesion by tapping with a hammer.</p>						
<b>Cleaning of Tools</b>	Clean all tools and application equipment with Sika® Colma Cleaner immediately after use. Hardened / cured material can only be mechanically removed.						
<b>Potlife</b>	<p>Potlife (200 g) (According to EN ISO 9514)</p> <table border="1"> <tr> <td>+10°C</td> <td>+23°C</td> <td>+30°C</td> </tr> <tr> <td>~ 180 minutes</td> <td>~ 60 minutes</td> <td>~ 40 minutes</td> </tr> </table> <p>The potlife begins when the resin and hardener are mixed. It is shorter at high temperatures and longer at low temperatures. The greater the quantity mixed, the shorter the potlife. To obtain longer workability at high temperatures, the mixed adhesive may be divided into portions. Another method is to chill parts A+B and C before mixing them (not below +5°C).</p>	+10°C	+23°C	+30°C	~ 180 minutes	~ 60 minutes	~ 40 minutes
+10°C	+23°C	+30°C					
~ 180 minutes	~ 60 minutes	~ 40 minutes					
<b>Notes on Application / Limitations</b>	Sikadur® resins are formulated to have low creep under permanent loading. However due to the creep behaviour of all polymer materials under load, the long term structural design load must account for creep. Generally the long term structural design load must be lower than 20-25% of the failure load. Please consult a structural engineer for load calculations for your specific application.						
<b>Value Base</b>	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.						
<b>Local Restriction</b>	Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the product uses.						
<b>Health and Safety Information</b>	For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.						
<b>Legal Notes</b>	The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.						



Sika Singapore Pte Ltd  
200 Pandan Loop, 06-02 Pantech 21  
Singapore 128388  
SINGAPORE

Phone: +65 6777 2811  
Fax: +65 6779 6200  
e-mail: [info@sg.sika.com](mailto:info@sg.sika.com)  
[www.sika.com.sg](http://www.sika.com.sg)



Sika Kimia Sdn Bhd  
Lot 689 Nilai Industrial Estate  
71800 Nilai, Negeri Sembilan DK  
MALAYSIA

Phone: +606-7991762  
Fax: +606-7991980  
e-mail: [info@my.sika.com](mailto:info@my.sika.com)  
[www.sika.com.my](http://www.sika.com.my)

