

# Sikagard®-61 TZ

## Epoxy splash zone coating

Construction

### Product Description

Sikagard®-61 TZ is a high performance solvent free, two part epoxy coating designed to provide corrosion resistance and abrasion protection in extreme service applications. This specially designed epoxy system has very high penetrating properties, flexibility and adhesion on wet concrete and steel substrate.

### Uses

Sikagard®-61 TZ is designed to provide corrosion protection for metal and concrete structures in offshore marine and petrochemical services, sheet piles, underground and submarine pipes, waste water tanks, jetty piles, underground tanks and other structural steel that requires protection against corrosion in aggressive environment.

It is most suitable for use where concrete surfaces are damp and cannot be dried out. Suitable for maintenance of splash and tidal zones.

### Advantages

- Deep penetration into concrete surface to avoid peeling
- High build – can be applied up to 250 microns in one coat
- Good resistance against mild chemicals
- Excellent adhesion to wet surface
- Cures under water after application
- Cures at low temperatures
- Excellent flexibility

### Product Data

#### Form

Appearance / Colour Grey, Black

Finish Gloss

Packaging 5 kg sets

#### Storage

Storage Condition / Shelf Life 2 years from the date of production if stored properly in original, unopened and undamaged sealed packaging in dry conditions. Keep away from direct sunlight.

#### Technical Data

Solids Content by Volume 98% ± 2%



## System Information

### Application Details

<b>Consumption</b>	<ul style="list-style-type: none"> <li>■ Recommended thickness is 200 microns DFT (500 microns for severe environment)</li> <li>■ Theoretical coverage is approx. 3.0 m<sup>2</sup> per kg at 200 microns DFT</li> <li>■ Recommended 2 coats</li> </ul>
--------------------	---

<b>Surface Preparation</b>	<p>Remove oil or grease from surface to be coated. Surface to be free from loose and friable materials.</p> <p><i>Steel</i></p> <p>For maximum protection, sand blast to remove surface contaminants and create surface profile about 50 to 75 microns.</p> <p><i>Concrete</i></p> <p>Wet blasting or high pressure water jet blasting is recommended to remove surface contaminants before application of coatings.</p>
----------------------------	--

### Application Instructions

<b>Mixing</b>	<p>Mix part A thoroughly then mix in part B and mix till homogeneous. Do not break sets.</p> <p><i>Thinning is not recommended.</i></p>
---------------	---

<b>Application Method / Tools</b>	Sikagard <sup>®</sup> -61 TZ can be applied by brush, roller or spray.
-----------------------------------	--

<b>Pot Life</b>	60 minutes (varies with temperature)
-----------------	--------------------------------------

<b>Cleaning of Tools</b>	Clean all tools and application equipment with Thinner-C immediately after use. Hardened and/or cured material can only be mechanically removed.
--------------------------	--

### Curing Details

<b>Curing</b>	<ul style="list-style-type: none"> <li>■ Touch dry                      2 hours (at + 20°C)</li> <li>■ Topcoat                         12 hours (at +20°C)</li> <li>■ Full Cure                        7 days (at 20°C)</li> </ul>
---------------	--

<b>Value Base</b>	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.
-------------------	--

<b>Health and Safety Information</b>	For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet (available upon request) containing physical, ecological, toxicological and other safety-related data.
--------------------------------------	--

<b>Legal Note</b>	<p>The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.</p>
-------------------	---



Sika Kimia Sdn Bhd  
 Lot 689 Nilai Industrial Estate  
 71800 Nilai, Negeri Sembilan DK  
 MALAYSIA

Phone: +606-7991762  
 Fax: +606-7991980  
 e-mail: [info@my.sika.com](mailto:info@my.sika.com)  
[www.sika.com.my](http://www.sika.com.my)

